



53 C Otis Street  
West Babylon, NY 11704  
Tel. 631-920-5079 Fax. 631-920-0503  
E-mail SalesSET@optonline.net  
www.SET-mfg.com

## Set-Sil 8429 Platinum Gel

**Set-Sil 8429** Platinum Gel is an extremely soft, tacky, transparent, resilient silicone rubber gel. It is a two component, addition cure material that is sensitive to cure inhibition when in contact with sulfur, nitrogen or organo-tin containing materials. **Set-Sil 8429** has a low viscosity that allows for easy mixing, deairing, and pouring. It is used for potting or encapsulating electrical parts where visual inspection is required. It has excellent electrical insulating properties and provides superior damping characteristics. **Set-Sil 8429** has greater mechanical properties than traditional gels and can be used in conjunction with platinum cured special effect silicones to produce realistic simulations of living tissue.

### MIXING INSTRUCTIONS

Mix 100 parts by weight of **Set-Sil 8429** Base with 100 parts by weight of **Set-Sil 8429** Activator in a container that will hold about two times the volume of the rubber being mixed. Stir thoroughly either by hand or by mechanical means, taking care to scrape the sides and bottom of the container. Immediately after mixing, place the container in a vacuum chamber capable of 28 inches of mercury vacuum. The rubber will expand as it is being deaired. After the rubber collapses, maintain the vacuum for an additional two minutes and release. Carefully pour the catalyzed silicone rubber gel into the mold cavity. Be sure to seal anything that may cause inhibition.

### TYPICAL PROPERTIES

Color, base	Transparent
Color, activator	Transparent
Base viscosity (cps)	7,000
Activator viscosity (cps)	7,000
Working Time (hrs)	2 to 4
Cure Time (hrs)	18 to 24
Specific Gravity, cured rubber	1.00
Penetrometer Measurement (mm)	
1 day	40 - 60
7 days	50 - 70
Shrinkage (%)	nil
Tensile Strength (psi)	< 100
Elongation (%)	>500
Dielectric Strength (volts/mil)	500
Dielectric Contant @ 100 Hz	2.9
Dissipation Factor @ 100 Hz	0.003
Volume Resistivity (ohmx/cm)	1 x 10 <sup>15</sup>
Shelf Life (uncured material)	6 months

See Back of Data Sheet for Warranty

## **Warranty**

**Silicone & Epoxy Technology** accepts no liability, in negligence or otherwise, in this communication. Under no circumstances shall the company be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability or any other theory, arising out of the use or handling of this product. The sole liability shall be the purchase price of the product. You should test the material to determine if the material is suitable, and/or claims are valid, in your particular circumstances. None of the possible or suggested uses of the materials in this communication are licensed under any Silicone & Epoxy Technology patent covering such use or a recommendation for use of such materials in the infringement of any patent.

### **Silicone & Epoxy Technology**

Phone: 631-920-5079      Fax: 631-920-0503

**Place Orders To: SalesSET@optonline.net**

**www.SET-mfg.com**