



Silicone & Epoxy Technology

53 C Otis Street
West Babylon, NY 11704
Tel. 631-920-5079 Fax. 631-920-0503
SalesSET@optonline.net
www.SET-mfg.com

Set-Sil 846

Low Density RTV Silicone Compound

Set-Sil 846 finds use in applications involving air-bourne or “man-pack” equipment. **Set-Sil 846** is suggested for use in circuitry requiring low capacitance, low dielectric constant and low dissipation.

Properties-Uncured

Color, visual	White
Viscosity, cps	40,000±2000
Specific Gravity	0.72
Mix Ratio	100:10
Pot life @ 25° C, hrs	2-3
Shelf Life @ 25° C, months	6

Physical Cured Properties

Durometer, Shore A	30
Tensile Strength, psi	700 min
Tensile Elongation,%	120 min
Coefficient of Thermal Expansion	2.0 X 10 ⁻⁴
Thermal Conductivity, BTU-ft(ft ²)(hr)(°F)	0.15
Service Temperature, °C	-55 to 204

Electrical

Dielectric Strength, Volts/mil	500
Dielectric Constant, 1 KHz	2.6
Dissipation Factor, 1 KHz	0.004
Volume Resistivity, Ohm-cm	1 X 10 ¹⁴

Mixing Instruction:

Weigh out the required amount of Set-Sil 846 A and B by weight. Mix Thoroughly, scrapping both the bottom and sides of the mixing container. Evacuate mixture @ 29 in Hg until all air is released to insure void-free casting.

Cure Schedule:

Cure overnight at room temperature 73°F (25°C).

SEE BACK OF TECHNICAL DATA SHEET FOR WARRANTY

Warranty

Silicone & Epoxy Technology accepts no liability, in negligence or otherwise, in this communication. Under no circumstances shall the company be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability or any other theory, arising out of the use or handling of this product. The sole liability shall be the purchase price of the product. You should test the material to determine if the material is suitable, and/or claims are valid, in your particular circumstances. None of the possible or suggested uses of the materials in this communication are licensed under any Silicone & Epoxy Technology patent covering such use or a recommendation for use of such materials in the infringement of any patent.

Silicone & Epoxy Technology

Phone: 631-920-5079 Fax: 631-920-0503

Place Orders To: SalesSET@optonline.net

www.SET-mfg.com