



53 C Otis Street
 West Babylon, NY 11704
 Tel. 631-920-5079 Fax. 631-920-0503
 E-mail SalesSET@optonline.net
 www.SET-mfg.com

Set-Cast 1-333 HTC

FLAME RETARDANT EPOXY CASTING COMPOUND

DESCRIPTION

Set-Cast 1-333 HTC is a 100% solids epoxy system. It is a filled, general-purpose epoxy encapsulant and casting compound. Polycast 133 has excellent moisture resistance and is machine dispensable and is flame retardant.

PROPERTIES – UNCURED

	Part A	Part B
Color , visual	Black	Amber
Viscosity, ASTM-D-2393 (c.p.s. @ 25° C)..	20,000	650-700
Specific Gravity	1.6	1.00
Mix Ratio (by weight)	100:9	
Mixed Viscosity, ASTM-D-2393 (@ 25° C)	10000	
Pot Life @ 25°C (100 grams)	60 minutes	
Shelf Life @ 70° F	12 months minimum	

PROPERTIES – CURED

Hardness, ASTM-D-2240(Durometer).....	Shore D 86
Tensile Strength, ASTM-D-638	11,500 psi
Tensile Elongation, ASTM-D-638	2.8 %
Flexural Strength, ASTM-D-790.....	17,500 psi
Coefficient of Thermal Expansion	48 x 10 ⁻⁶
Water Absorption.....	0.08%
Dielectric Strength, ASTM-D-149 (volts/mil)	415
Dielectric Constant, ASTM-D-150	4.4
Dissipation Factor, ASTM-D-150.....	0.02
Volume Resistivity, ASTM-D-257 (ohm-cm).....	1 x 10 ¹⁵
Thermal Conductivity, BTU's.....	10

MIXING INSTRUCTIONS

Pre-mix Part A separately. Then measure 100:9 parts by weight (A to B). Mix thoroughly scraping the sides and bottom of the container. Evacuate and then pour into mold or cavity.

CURE SCHEDULE

Room temperature cure @75°F with full properties after 24 hours.
 To accelerate cure, allow 2 hours @ room temperature, then 2 hours @ 125°F.

See back of Data Sheet for Warranty Information

Warranty

Silicone & Epoxy Technology accepts no liability, in negligence or otherwise, in this communication. Under no circumstances shall the company be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability or any other theory, arising out of the use or handling of this product. The sole liability shall be the purchase price of the product. You should test the material to determine if the material is suitable, and/or claims are valid, in your particular circumstances. None of the possible or suggested uses of the materials in this communication are licensed under any Silicone & Epoxy Technology patent covering such use or a recommendation for use of such materials in the infringement of any patent.

Silicone & Epoxy Technology

Phone: 631-920-5079 Fax: 631-920-0503

Place Orders To: SalesSET@optonline.net

www.SET-mfg.com