



Silicone & Epoxy Technology

53 C Otis Street
West Babylon, NY 11704
Tel. 631-920-5079 Fax. 631-920-0503
E-mail: SalesSET@optonline.net
www.SET-mfg.com

Set-SIE 3075 Polyurethane Elastomer

Set-SIE 3075 is a tough, impact resistant elastomer formulated for room temperature hand-batch mixing. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury, MOCA or TDI.

TYPICAL PROPERTIES:

Resin/Hardener ratio (Parts by Weight)	100/89
Resin/Hardener ratio (Parts by Volume)	100/100
Resin viscosity (@ 77° F.)	75cps
Hardener viscosity (@ 77° F.)	850 cps
Initial mixed viscosity	300 cps
Working life (@ 77° F.)	8 ± 2 Min.
Color	Translucent
Demold time	60 ± 30 Min.
Ultimate cure @ 77° F.	7 days
Specific Gravity (Hardener)	1.25 (gm/cc)
(Resin)	1.11 (gm/cc)
(Mixed)	1.11 (gm/cc)

CURED PROPERTIES

	<u>Test Method</u>	24 Hrs. @ 77° F. & 16 Hrs @ 200° F.	7 days @77° F
Hardness	ASTM D-2240	80-85 D	80-85 D
Tensile Strength	ASTM D-638	10000 psi	10500 psi
Elongation at Break	ASTM D-638	9 %	8 %
Tensile Modulus	ASTM D-638	165000 psi	165000 psi
Notched Izod	ASTM D-256	0.7 ft.lbs/in.	0.7 ft.lbs/in.
Linear Shrinkage in./in.	ASTM D-2566	0.002-0.004	0.002-0.004
Ultimate Flex Strength	ASTM D-790	16500 psi	17000 psi
Flex Modulus	ASTM D-790	390000 psi	420000 psi
Heat Deflection Temp (66psi)	ASTM D-648	83°C/182° F	77°C/171° F
Heat Deflection Temp (264psi)	ASTM D-648	n/a	n/a

Agitate hardener and resin before mixing to ensure that the formula is homogeneous.

Read Warranty on Back of Technical Data Sheet.

Warranty

Silicone & Epoxy Technology accepts no liability, in negligence or otherwise, in this communication. Under no circumstances shall the company be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability or any other theory, arising out of the use or handling of this product. The sole liability shall be the purchase price of the product. You should test the material to determine if the material is suitable, and/or claims are valid, in your particular circumstances. None of the possible or suggested uses of the materials in this communication are licensed under any Silicone & Epoxy Technology patent covering such use or a recommendation for use of such materials in the infringement of any patent.

Silicone & Epoxy Technology

Phone: 631-920-5079 Fax: 631-920-0503

Place Orders To: SalesSET@optonline.net

www.SET-mfg.com