



53 C Otis Street  
West Babylon, NY 11704  
Tel. 631-920-5079 Fax. 631-920-0503  
E-mail SalesSET@optonline.net  
www.SET-mfg.com

## Set-Sil 860 SILICONE RUBBER

**Set-Sil 860** is a two component addition cure silicone rubber mold making material. It has a high durometer, superb physical properties, minimal shrinkage and extreme chemical resistance making it an excellent choice for prototyping, casting urethane foam and other plastics. **Set-Sil 860** cures at room temperature in 18-24 hours; however, the curing rate can be accelerated with Pt Accelerator at room temperature or with heat.

### MIXING INSTRUCTIONS

Mix 10 parts by weight of **Set-Sil 860** Base with 1 part by weight of **Set-Sil 860** Activator in a container that will hold about three times the volume of the rubber being mixed. Stir thoroughly either by hand or by mechanical means until a uniform blue color is achieved. Immediately after mixing, place the container in a vacuum chamber capable of 28 inches of mercury vacuum. The rubber will expand to double or triple its original volume as it is being deaired. After the rubber collapses, maintain the vacuum for an additional two minutes and then release. Carefully pour the catalyzed silicone rubber over the released pattern.

### TYPICAL PROPERTIES

Color, Base	Tan
Color, Activator	Blue
Base viscosity (cps)	130,000-150,000
Activator viscosity (cps)	7500 - 8500
Working Time (hrs)	1 to 2
Cure Time (hrs)	18 to 24
Specific Gravity, cured rubber	1.24
Shore A Hardness	
24 hours @ 70° F/50% R.H.	62 ± 3
+ 2 hours @ 250° F	68 ± 3
Tear Resistance (ppi)	70 ± 10
Tensile Strength (psi)	900 ± 50
Elongation (%)	200 ± 25
Shrinkage (%)	nil

**Warranty**

**Silicone & Epoxy Technology** accepts no liability, in negligence or otherwise, in this communication. Under no circumstances shall the company be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability or any other theory, arising out of the use or handling of this product. The sole liability shall be the purchase price of the product. You should test the material to determine if the material is suitable, and/or claims are valid, in your particular circumstances. None of the possible or suggested uses of the materials in this communication are licensed under any Silicone & Epoxy Technology patent covering such use or a recommendation for use of such materials in the infringement of any patent.

**Silicone & Epoxy Technology**

Phone: 631-920-5079      Fax: 631-920-0503  
Place Orders To: [SalesSET@optonline.net](mailto:SalesSET@optonline.net)  
[www.SET-mfg.com](http://www.SET-mfg.com)