



53 C Otis Street  
 West Babylon, NY 11704  
 Tel. 631-920-5079 Fax. 631-920-0503  
 E-mail SalesSET@optonline.net  
 www.SET-mfg.com

## Set-Sil RTVP 216 Optically Clear Silicone

**Set-Sil RTVP 216** is a low viscosity, optically clear silicone rubber used for potting or encapsulation of intricate parts where visual inspection is required. **Set-Sil RTVP 216** offers electrical stability, radiation resistance and will resist reversion when heated in confined spaces. Although it has high tensile strength, it can be easily cut and removed for part repair and new material poured.

<b>Color</b>	<b>CLEAR</b>
<b>Viscosity, cps</b>	<b>4000</b>
<b>Specific Gravity</b>	<b>1.02</b>
<b>Mix Ratio by weight</b>	<b>10 to 1</b>
<b>Pot Life @ 25°C, Hours</b>	<b>4</b>
<b>Durometer, Shore A</b>	<b>40</b>
<b>Tensile Strength, psi</b>	<b>750</b>
<b>Tensile Elongation,%</b>	<b>100</b>
<b>Shrinkage,%</b>	<b>nil</b>
<b>Coefficient of Thermal Expansion</b>	<b>27.5 x 10<sup>-5</sup></b>
<b>Thermal Conductivity, BTU-ft/(ft<sup>2</sup>)(hr)(°F)</b>	<b>1.32</b>
<b>Service temperature Range °C</b>	<b>-55-204°C</b>
<b>Dielectric Strength, volts/mil</b>	<b>500</b>
<b>Dielectric Constant, 1KHz</b>	<b>2.69</b>
<b>Dissipation Factor, 1 KHz</b>	<b>0.0006</b>
<b>Volume Resistivity, ohm-cm</b>	<b>1.7x 10<sup>15</sup></b>
<b>Refractive Index</b>	<b>1.406</b>

### Mixing Instruction:

Weigh out the required amount of *Set-Sil RTVP 216 A* and *B*. Mix thoroughly, scraping both the bottom and sides of the mixing container. Evacuate mixture @ 29 in Hg until all air is released to insure void-free casting.

### Cure Schedule:

<b>70°F:</b>	<b>125°F:</b>	<b>150°F:</b>	<b>200°F:</b>	<b>250°F:</b>	<b>300°F:</b>
<b>24 Hrs.</b>	<b>1.5 Hrs.</b>	<b>45 Min.</b>	<b>25 Min.</b>	<b>15 Min.</b>	<b>10 Min.</b>

**SEE BACK OF TECHNICAL DATA SHEET FOR WARRANTY.**

## **Warranty**

**Silicone & Epoxy Technology** accepts no liability, in negligence or otherwise, in this communication. Under no circumstances shall the company be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability or any other theory, arising out of the use or handling of this product. The sole liability shall be the purchase price of the product. You should test the material to determine if the material is suitable, and/or claims are valid, in your particular circumstances. None of the possible or suggested uses of the materials in this communication are licensed under any Silicone & Epoxy Technology patent covering such use or a recommendation for use of such materials in the infringement of any patent.

### **Silicone & Epoxy Technology**

Phone: 631-920-5079      Fax: 631-920-0503

Place Orders To: SalesSET@optonline.net

**[www.SET-mfg.com](http://www.SET-mfg.com)**